

250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 psa.tape@averydennison.com email: URL: tapes.averydennison.com

## TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resi 2.2, Heat Resistance, Initial, 2

SECTION: 3.0 **Heat Resi** 2.2, Heat Resistance, 168 hrs @

SECTION: 3.0 **Heat Resi** 2.2, Heat Resistance, 8 hrs @

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

Page 1 of 1

## TEST REPORT

FT 333

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

LYTHERM E-COATED METAL 230103 - 1056

## FCA PF.90175

OEM Rev Date: Mar 15 Pressure Sensitive Adhesives Includes Chrysler Standard PF-10770 Table 2 Flexible Composites

ACCREDITED

TESTING LABORATORY

sistance	Specification	<u>Results</u>	<u>Status</u>
2 hrs @ RT	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
sistance	Specification	<u>Results</u>	<u>Status</u>
a @ 79⁰C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
sistance	Specification	<u>Results</u>	<u>Status</u>
) 93°C"	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass

Specification No Adhesion Loss or Lifting

Specification No Adhesion Loss or Lifting

Stable, No Lift or Adhesion Loss	Pas

Results Status Stable, No Lift or Adhesion Loss Pass

Results Status Stable, No Lift or Adhesion Loss Pass

Specification	Results	<u>Status</u>
0.9 N / cm	2.4	Pass
Specification	Results	<u>Status</u>
3.3 N / cm	8.3	Pass
Specification	<u>Results</u>	<u>Status</u>
3.3 N / cm	10.4	Pass
Specification	Results	<u>Status</u>
3.3 N / cm	4.0	Pass
Specification	<u>Results</u>	<u>Status</u>
3.3 N / cm	9.6	Pass

ISSUE DATE:

1-1-25

7-11-2017