

 250 Chester Street

 Painesville, Ohio 44077

 Phone:
 866-GO-AVERY (866-462-8379)

 Fax:
 888-358-4469

 email:
 psa.tape@averydennison.com

 URL:
 tapes.averydennison.com

TAPE REQUIREMENTS:

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: **3.0 Heat Resistance** 2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, 168 hrs @ 79°C

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, 8 hrs @ 93°C

SECTION: **3.0 Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

SECTION: **3.0 Peel Adhesion** 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Techniclan

FCA PF.90175 OEM Rev Date: Mar 15

230103 - 1057

TEST REPORT

FT 702P

SS

NITRILE VINYL FOAM

Pressure Sensitive Adhesives Includes Chrysler Standard PF-10770 Table 2 Flexible Composites

PRODUCT:

SUPPORT:

CERT NO .:

SUBSTRATE:

| Specification | | | |
|-----------------------------|--|--|--|
| No Adhesion Loss or Lifting | | | |

Specification No Adhesion Loss or Lifting

ANSI National Accreditation Board A C C R E D I T E D ISO/IEC 17025 TESTING LABORATORY

| <u>Results</u> | <u>Status</u> |
|----------------------------------|---------------|
| Stable, No Lift or Adhesion Loss | Pass |

Status

Pass

Status

Pass

<u>Results</u> Stable, No Lift or Adhesion Loss

Results Stable, No Lift or Adhesion Loss

ResultsStatusStable, No Lift or Adhesion LossPass

ResultsStatusStable, No Lift or Adhesion LossPass

| Specification | <u>Results</u> | <u>Status</u> |
|---------------|----------------|---------------|
| 0.9 N / cm | 5.5 | Pass |
| Specification | <u>Results</u> | <u>Status</u> |
| 3.3 N / cm | 10.6 | Pass |
| Specification | <u>Results</u> | <u>Status</u> |
| 3.3 N / cm | 8.7 | Pass |
| Specification | <u>Results</u> | <u>Status</u> |
| 3.3 N / cm | 7.9 | Pass |
| Specification | <u>Results</u> | <u>Status</u> |
| 3.3 N / cm | 4.1 | Pass |

ISSUE DATE:

1-1-25

7-11-2017

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: