

250 Chester Street Painesville, Ohio 44077 Phone: **866-GO-AVERY (866-462-8379)** Fax: **888-358-4469** email: **psa.tape@averydennison.com** URL: **tapes.averydennison.com**

TAPE REQUIREMENTS:

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: **3.0 Heat Resistance** 2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, 168 hrs @ 79°C

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, 8 hrs @ 93°C

SECTION: **3.0 Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

SECTION: **3.0 Peel Adhesion** 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Techniclan

TEST REPORT

FT 8217

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.:

FCA PF.90175

N

OEM Rev Date: Mar 15

NITRILE VINYL FOAM <mark>SS</mark> 230103 - 1124



Pressure Sensitive Adhesives			
Includes Chrysler Standard PF-10770			
Table 2 Flexible Composites			

Specification			
0	Adhesion Loss or Lifting		

Specification No Adhesion Loss or Lifting

ResultsStatusStable, No Lift or Adhesion LossPass

Status

Pass

Status

Pass

<u>Results</u> Stable, No Lift or Adhesion Loss

<u>Results</u> Stable, No Lift or Adhesion Loss

ResultsStatusStable, No Lift or Adhesion LossPass

ResultsStatusStable, No Lift or Adhesion LossPass

Specification	Results	<u>Status</u>
0.9 N / cm	17.8	Pass
Specification	<u>Results</u>	<u>Status</u>
3.3 N / cm	18.0	Pass
Specification	<u>Results</u>	<u>Status</u>
3.3 N / cm	15.8	Pass
Specification	Results	<u>Status</u>
3.3 N / cm	3.3	Pass
Specification	<u>Results</u>	<u>Status</u>
3.3 N / cm	16.5	Pass

ISSUE DATE:

<u>1-1-25</u>

7-12-2017

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: