

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email: URL:

tapes.averydennison.com

TEST REPORT

PRODUCT: **FBA 8960**

CRUSHED EPDM SUPPORT:

SUBSTRATE: PC ASA

CERT NO.: 230103 - 1141

FCA PF.90175

OEM Rev Date: Mar 15 Pressure Sensitive Adhesives

Includes Chrysler Standard PF-10770

Table 2 Flexible Composites



TAPE REQUIREMENTS:

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 168 hrs @ 79°C

Heat Resistance SECTION: 3.0 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

No Adhesion Loss or Lifting

Specification

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Specification

Specification

0.9 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

No Adhesion Loss or Lifting

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

6.2

Status Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 **Peel Adhesion**

3.0, Adhesion, 168 hrs @ 79°C

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion**

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion**

3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

Results

Results 5.7

Results

5.8

Results 6.5

Results Status 4.4 **Pass**

Page 1 of 1

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.