

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

FT 7515
PET FOAM
ABS
221209 - 0915



FORD ESA-M11P19-A OEM Rev Date: Dec 13 Adhesion Requirements Polyurethane Foam to Polypropylene - Pressure Sensitive Film

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials SECTION 3.1 Peel Strength, Plastic Membrane to Panel 3.1.1, As Received	Specification 0.44 N / mm	ASTM D903	<u>Results</u> 0.96	<u>Status</u> Pass
SECTION 3.1 Peel Strength, Plastic Membrane to Panel 3.1.2, Aged, Heat Aged, 7 days @ 88°C	Specification 0.44 N / mm	ASTM D903	<u>Results</u> 1.31	<u>Status</u> Pass
SPEC: 3.1 Peel Strength, Plastic Membrane to Panel 3.1.2, Humidity, 7 days @ 37°C / 95% RH	Specification 0.44 N / mm	ASTM D903	<u>Results</u> 1.14	<u>Status</u> Pass
SECTION 3.2 Peel Strength, Foam to Plastic Membrane 3.2.1, Foam to Plastic Membrane, As Received	Specification No Delamination	ASTM D903	<u>Results</u> NA	<u>Status</u> NA

Specification	ASTM D1000	<u>Results</u>	<u>Status</u>
	n Actual	NT	Not Tested
)		Separation of Bond From an Actual	Separation of Bond From an Actual NT

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

6-16-2015 Page 1 of 1