



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: stus.averydennison.com

PRODUCT: FT 1149X
SUPPORT: PEU FOAM
SUBSTRATE: PP
CERT NO.: 221209 - 1309



FORD ESB-M11P8-A
OEM Rev Date: Dec 13
Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

ASTM D903

SECTION 3.1 Adhesion

Specification

Results

Status

3.1.1, As Received

0.66 N / mm

1.04

Pass

SECTION 3.1 Adhesion

Specification

Result

Status

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

0.22 N / mm

0.68

Pass

SECTION 3.1 Adhesion

Specification

Result

Status

3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

0.44 N / mm

0.48

Pass

CERTIFIED BY:

Signature of Jake Cowdrick
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.