TEST REPORT



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 0400
SUPPORT: PET
SUBSTRATE: PP

CERT NO.: 221209 - 0910

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TΛ	DE	DE		DEN	IEN.	TC.
IA	PE	RE	wu	REI		13:

TAPE REQUIREMENTS.				
SECTION 3.6.1 Peel Adhesion	ASTM D3330	Specification	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT		219 N/m	1029.7	Pass
SECTION 3.6.2 Aged	ASTM D3330	<u>Specification</u>	Results	<u>Status</u>
3.6.2, Aged, Aged, 72 hrs @ RT		657 N/m	1061.9	Pass
OFOTION 262 Annal Cycles	40TM D0000	Specification	Beaulte	04-4
SECTION 3.6.3 Aged, Cycles	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.3, Aged, Cycles, CycleTest (5x)		438 N/m	875.6	Pass
4 hrs @ 70° C				
4 hrs @ 38° C / 95% RH				
16 hrs @ -29° C				
16 hrs @ -29° C				
16 hrs @ -29° C 4 hrs @ 38° C / 95% RH				

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Stai	n, 48 Hour Fluorescence,	White Enamel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D3330	Specification	Results	<u>Status</u>
3.8, Liner Remov	al, Initial Release		55 N/m	30.9	Pass

SECTION 3.9 Storage Stability Specification Results Status
3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: <u>1-1-25</u>

3-27-2002

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.