TEST REPORT



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1126
SUPPORT: PEU FOAM
SUBSTRATE: ABS

CERT NO.: 221209 - 0842

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TΛ	DE	DE	OI I	IDEI	MEN	ITS:
IA	PE	RE	ωu	ᇚᇊ	יוםוע	113:

	TAPE REQUIREMENTS.					
	SECTION 3.6.1 Peel Adhesion	ASTM D3330	Specification	<u>Results</u>	<u>Status</u>	
3.6.1, Peel Adhesion, As Received, Initial RT			219 N/m	1050.8	Pass	
	SECTION 3.6.2 Aged	ASTM D3330	Specification	Results	Status	
	•	A31W D3330				
3.6.2, Aged, Aged, 72 hrs @ RT		657 N/m		1050.8	Pass	
	SECTION 3.6.3 Aged, Cycles	ASTM D3330	Specification	Results	<u>Status</u>	
	SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x)	ASTM D3330	Specification 438 N/m	<u>Results</u> 1050.8	Status Pass	
		ASTM D3330				
	3.6.3, Aged, Cycles, CycleTest (5x)	ASTM D3330				
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C	ASTM D3330				
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH	ASTM D3330				
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C	ASTM D3330				
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH	ASTM D3330				

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Stain, 48 Hour Fluorescence, White Enamel			None	Not Applicable	NA
SECTION 3.8	Liner Removal	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.8, Liner Remova	al, Initial Release		55 N/m	33.3	Pass

SECTION 3.9 Storage Stability Specification Results Status
3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: <u>1-1-25</u>

5-22-2002

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.