TEST REPORT



250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

psa.tape@averydennison.com email: URL: tapes.averydennison.com

FT 1143 PRODUCT: SUPPORT: **PVC FOAM** SUBSTRATE: PP

221209 - 0842 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TΛ	DE	DE	OI I	IDEI	MEN	ITS:
IA	PE	RE	ωu	ᇚᇊ	יוםוע	113:

	TAPE REQUIREMENTS:				
	SECTION 3.6.1 Peel Adhesion	ASTM D3330	Specification	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT			219 N/m	305.3	Pass
	SECTION 3.6.2 Aged	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	3.6.2, Aged, Aged, 72 hrs @ RT		657 N/m	1210.7	Pass
	SECTION 3.6.3 Aged, Cycles	ASTM D3330	Specification	Results	<u>Status</u>
	SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x)	ASTM D3330	Specification 438 N / m	<u>Results</u> 1087.0	Status Pass
		ASTM D3330			
	3.6.3, Aged, Cycles, CycleTest (5x)	ASTM D3330			
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C	ASTM D3330			
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH	ASTM D3330			
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C	ASTM D3330			
	3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH	ASTM D3330			

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Stai	n, 48 Hour Fluorescence,	White Enamel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D3330	Specification	Results	<u>Status</u>
3.8, Liner Remov	al, Initial Release		55 N/m	23.9	Pass

SECTION 3.9 **Storage Stability Specification** Results **Status** Not Tested 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference **TBD**

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

1-1-25 ISSUE DATE:

7-2-2002

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.