

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT:	FT 4305
SUPPORT:	PRODUCT
SUBSTRATE:	PP
CERT NO .:	221209 - 0842

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:SECTION 3.6.1Peel Adhesion3.6.1, Peel Adhesion, As Received, Initial RT	ASTM D3330	Specification 219 N / m	<u>Results</u> 1438.4	<u>Status</u> Pass
SECTION 3.6.2 Aged	ASTM D3330	Specification	<u>Results</u>	<u>Status</u>
3.6.2, Aged, Aged, 72 hrs @ RT		657 N / m	1482.7	Pass
SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	ASTM D3330	Specification 438 N / m	<u>Results</u> 1496.8	<u>Status</u> Pass
SECTION 3.7 Migration Stain	FLTM BO 115-1*	Specification	<u>Results</u>	<u>Status</u>
3.7, Migration Stain, 48 Hour Fluorescence, White E	namel	None	Not Applicable	NA
SECTION 3.8 Liner Removal	ASTM D3330	Specification	Results	<u>Status</u>
3.8, Liner Removal, Initial Release		55 N / m	23.4	Pass

SECTION 3.9 **Storage Stability Specification** 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference

TBD

Status

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Results

Not Tested

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

3-27-2002 Page 1 of 1