250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

psa.tape@averydennison.com email: URL: tapes.averydennison.com

TEST REPORT

FT 8302 PRODUCT: SUPPORT: **EPDM FOAM**

SUBSTRATE: **ABS**

221209 - 0842 CERT NO.:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TΛ	DE	DE		DEN	IEN.	TC.
IA	PE	RE	wu	REI		13:

SECTION 3.6.1 Peel Adhesion	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT		219 N/m	943.9	Pass
SECTION 3.6.2 Aged 3.6.2, Aged, Aged, 72 hrs @ RT	ASTM D3330	Specification 657 N/m	<u>Results</u> 1538.8	Status Pass
SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C	ASTM D3330	Specification 438 N/m	<u>Results</u> 962.0	Status Pass

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C 16 hrs @ -29° C

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	in, 48 Hour Fluorescence,	White Enamel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D3330	Specification	<u>Results</u>	<u>Status</u>
3.8, Liner Remova	al, Initial Release		55 N/m	16.3	Pass

SECTION 3.9 **Storage Stability Specification** Results **Status TBD**

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

1-1-25 ISSUE DATE:

5-11-2005

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.