

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TAPE REQUIREMENTS:

## **TEST REPORT**

 PRODUCT:
 FT 8302

 SUPPORT:
 EPDM FOAM

 SUBSTRATE:
 SS

 CERT NO.:
 221209 - 0842



866-GO-AVERY (866-462-8379)888-358-4469FORD ESB-M3G76-B2psa.tape@averydennison.comOEM Rev Date: Sep 05tapes.averydennison.comTape, PET - Two Sided PSA

## SECTION 3.6.1 Peel Adhesion ASTM D3330 **Specification Results** Status 219 N/m 1081.1 3.6.1, Peel Adhesion, As Received, Initial RT Pass SECTION 3.6.2 Specification Results Aged ASTM D3330 Status 3.6.2, Aged, Aged, 72 hrs @ RT 657 N/m 1640.9 Pass SECTION 3.6.3 Aged, Cycles Specification ASTM D3330 Results Status 438 N/m 1386.4 3.6.3, Aged, Cycles, CycleTest (5x) Pass 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C SECTION 3.7 **Migration Stain** FLTM BO 115-1\* Specification **Results** Status Not Applicable 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel None NA

SECTION 3.8Liner RemovalASTM D3330SpecificationResultsStatus3.8, Liner Removal, Initial Release55 N / m16.3Pass

SECTION 3.9Storage StabilityStorage StabilityResultsStatus3.9, Storage Stability, Liner Removal after 12 Months Below 32°CNo Appreciable DifferenceNot TestedTBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

<u>1-1-25</u>

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: