

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: stus.averydennison.com

TEST REPORT

PRODUCT: FT 8327 SUPPORT: EPDM FOAM

SUBSTRATE: ABS

STD CERT NO.: 221209 - 0848

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA ANSI National Accreditation Board
A C C R E D | T E D

ISO/IEC 17025
TESTING LABORATORY

TAPE	REQU	JIREN	IEN	TS:
------	------	-------	-----	-----

SECTION 3.6.1 Peel Adhesion 3.6.1, Peel Adhesion, As Received, Initial RT	ASTM D3330	Specification 219 N/m	Results 922.9	Status Pass
S.C.1, 1 SCI Adriesion, As Acceived, initial A		2.0	022.0	1 433
SECTION 3.6.2 Aged	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.2, Aged, Aged, 72 hrs @ RT		657 N/m	1319.9	Pass
SECTION 3.6.3 Aged, Cycles	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x)	ASTM D3330	Specification 438 N/m	<u>Results</u> 1026.8	Status Pass
	ASTM D3330			
3.6.3, Aged, Cycles, CycleTest (5x)	ASTM D3330			
3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C	ASTM D3330			
3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH	ASTM D3330			
3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C	ASTM D3330			

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	in, 48 Hour Fluorescence, Wh	ite Enamel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D3330	<u>Specification</u>	Results	<u>Status</u>
3.8, Liner Removal,	, Initial Release		55 N/m	21.0	Pass

SECTION 3.9 Storage Stability Specification Results
3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 1-8-2013

Page 1 of 1