

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

stus.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

 PRODUCT:
 FT 8327

 SUPPORT:
 EPDM FOAM

 SUBSTRATE:
 PP

 STD CERT NO.:
 221209 - 0848

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA



TAPE REQUIREMENTS: SECTION 3.6.1 Peel Adhesion ASTM D3330 **Specification Results** Status 3.6.1, Peel Adhesion, As Received, Initial RT 219 N/m 749.5 Pass **Specification Results** SECTION 3.6.2 Aged ASTM D3330 Status 3.6.2, Aged, Aged, 72 hrs @ RT 657 N/m 1051.3 Pass SECTION 3.6.3 Aged, Cycles Specification Results ASTM D3330 Status 438 N/m 1063.0 3.6.3, Aged, Cycles, CycleTest (5x) Pass 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C

tus	
NA	
4	
<u>tus</u>	
SS	
tu	

SECTION 3.9Storage StabilityStorage StabilityStorage StabilityResultsStatus3.9, Storage Stability, Liner Removal after 12 Months Below 32°CNo Appreciable DifferenceNot TestedTBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

<u>1-1-25</u>

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: