



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8392**
SUPPORT: **2 MIL PET**
SUBSTRATE: **ABS**
CERT NO.: **230109 - 1042**

FORD ESB-M3G76-B2
OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

SECTION	TEST DESCRIPTION	STANDARD	Specification	Results	Status
SECTION 3.6.1	Peel Adhesion 3.6.1, Peel Adhesion, As Received, Initial RT	ASTM D1000	219 N / m	1077.6	Pass
SECTION 3.6.2	Aged 3.6.2, Aged, Aged, 72 hrs @ RT	ASTM D1000	657 N / m	1185.6	Pass
SECTION 3.6.3	Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	ASTM D1000	438 N / m	1523.0	Pass
SECTION 3.7	Migration Stain 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel	FLTM BO 115-01*	None	Not Applicable	NA
SECTION 3.8	Liner Removal 3.8, Liner Removal, Initial Release	ASTM D1000	55 N / m	25.1	Pass
SECTION 3.9	Storage Stability 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C		No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.