

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

16 hrs @ -29° C

TEST REPORT

PRODUCT: FT 8392 SUPPORT: 2 MIL PET

SUBSTRATE: SS

CERT NO.: 230109 - 1042

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE	REQU	IIREN	1EN	TS:
------	------	-------	-----	-----

SECTION 3.6.1 Peel Adhesion	ASTM D1000	Specification	Results	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT		219 N/m	1229.4	Pass
SECTION 3.6.2 Aged	ASTM D1000	<b>Specification</b>	<u>Results</u>	<u>Status</u>
3.6.2, Aged, Aged, 72 hrs @ RT		657 N/m	1408.6	Pass
SECTION 3.6.3 Aged, Cycles	ASTM D1000	Specification	<u>Results</u>	<u>Status</u>
3.6.3, Aged, Cycles, CycleTest (5x)		438 N/m	1523.0	Pass
4 hrs @ 70° C				
4 hrs @ 38° C / 95% RH				
16 hrs @ -29° C				
4 hrs @ 38° C / 95% RH				
4 hrs @ 70° C				

SECTION 3.7	Migration Stain	FLTM BO 115-01*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	in, 48 Hour Fluorescence, W	hite Enamel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D1000	<u>Specification</u>	Results	<u>Status</u>
3.8, Liner Removal,	Initial Release		55 N/m	25.1	Pass

SECTION 3.9	Storage Stability	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.9, Storage Stab	ility, Liner Removal after 12 Months Below 32°C	No Appreciable Difference	Not Tested	TBD

**CERTIFIED BY:** 

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

7-23-2001

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

 $Status\ opinion\ based\ upon\ measurements\ obtained\ by\ personnel\ with\ appropriate\ training\ and\ professional\ experience.$ 

This laboratory is not accredited for the calibrations or tests marked \*.