

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

**TEST REPORT** 

PRODUCT: FBR 8950 12 PT BD

SUPPORT: PET FOAM

SUBSTRATE: PP

CERT NO.: 221209 - 0853

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA

ANSI National Accreditation Board
A C C R E D I T E D
ISONEC 17025
TESTING LABORATORY

TAPE REQUI	REMENTS:
------------	----------

SECTION 3.6.1 Peel Adhesion	ASTM D3330	<b>Specification</b>	<u>Results</u>	<u>Status</u>
3.6.1 Peel Adhesion As Received Initial RT		219 N/m	1482.2	Pass

SECTION 3.6.2 Aged	ASTM D3330	<u>Specification</u>	Results	<u>Status</u>
3.6.2 Ared Ared 72 hrs @ RT		657 N / m	2035.0	Dace

3.6.2, Aged, Aged, 72 hrs @ RT	657 N/m	2035.0	<b>Pass</b>

SECTION 3.6.3 Aged, Cycles	ASTM D3330	<u>Specification</u>	Results	<u>Status</u>
3.6.3, Aged, Cycles, CycleTest (5x)		438 N/m	2112.0	Pass

3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C

41115 @ 70 C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C 16 hrs @ -29° C

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	in, 48 Hour Fluorescenc	e, White Enamel	None	Not Applicable	NA

 ,	 		1.1	

SECTION 3.8	Liner Removal	ASTM D3330	Specification	Results	Status
3.8, Liner Remov	al, Initial Release		55 N/m	10.5	Pass

## SECTION 3.9 Storage Stability Specification Results Status

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: <u>1-1-25</u>

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.