

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FBR 8950** SUPPORT: **EPDM FOAM**

PP SUBSTRATE:

221209 - 0852 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TAPE REQUI	REMENTS:
------------	----------

SECTION 361

ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	219 N/m	753.6	Pass
ASTM D3330	Specification	<u>Results</u>	<u>Status</u>
	657 N/m	1108.6	Pass
		219 N / m ASTM D3330 Specification	219 N/m 753.6 ASTM D3330 Specification Results

SECTION 3.6.3 Aged, Cycles	ASTM D3330	<u>Specification</u>	Results	<u>Status</u>
3.6.3, Aged, Cycles, CycleTest (5x)		438 N/m	1039.7	Pass

4 hrs @ 70° C

Peel Adhesion

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C 16 hrs @ -29° C

SECTION 3.7	Migration Stain	FLTM BO 115-1*	Specification	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	in, 48 Hour Fluorescence	, White Enamel	None	Not Applicable	NA

SECTION 3.8 **Liner Removal** ASTM D3330 **Specification** Results **Status** 3.8, Liner Removal, Initial Release 2.3 55 N/m **Pass**

Storage Stability Specification SECTION 3.9 Results **Status**

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested **TBD**

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 2-14-2012 Page 1 of 1