

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FBR 8950**

SUPPORT: NITRILE VINYL FOAM

SUBSTRATE: PP

221209 - 0852 CERT NO.:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA ACCREDITED TESTING LABORATORY

659.6

Pass

Pass

Pass

TAPE REQUIREMENTS:

SECTION 3.6.1 Peel Adhesion **ASTM D3330 Specification Results Status**

3.6.1, Peel Adhesion, As Received, Initial RT 219 N/m 472.8

Specification Results SECTION 3.6.2 Aged ASTM D3330 **Status**

3.6.2, Aged, Aged, 72 hrs @ RT 657 N/m

SECTION 3.6.3 Aged, Cycles **Specification** Results **ASTM D3330 Status** 438 N/m 671.3

3.6.3, Aged, Cycles, CycleTest (5x)

4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C

16 hrs @ -29° C

SECTION 3.7 **Migration Stain** FLTM BO 115-1* **Specification** Results **Status**

Not Applicable 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel None NA

SECTION 3.8 **Liner Removal ASTM D3330 Specification** Results **Status**

2.3 3.8, Liner Removal, Initial Release 55 N/m **Pass**

Storage Stability SECTION 3.9 **Specification** Results **Status**

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested **TBD**

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

1-1-25 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: 2-14-2012 Page 1 of 1