

888-358-4469

SECTION 3.6.1 Peel Adhesion

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

3.6.1, Peel Adhesion, As Received, Initial RT

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TAPE REQUIREMENTS:

TEST REPORT

Specification

219 N/m

 PRODUCT:
 FBR 8950

 SUPPORT:
 PEU FOAM

 SUBSTRATE:
 PP

 CERT NO.:
 221209 - 0852



Status

Pass

Results

1844.1

FORD ESB-M3G76-B2 OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA

ASTM D3330

Specification Results SECTION 3.6.2 Aged ASTM D3330 Status 1992.4 3.6.2, Aged, Aged, 72 hrs @ RT 657 N/m Pass SECTION 3.6.3 Aged, Cycles Specification Results ASTM D3330 Status 438 N/m 1728.5 3.6.3, Aged, Cycles, CycleTest (5x) Pass 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C SECTION 3.7 **Migration Stain** FLTM BO 115-1* Specification Results Status Not Applicable 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel None NA SECTION 3.8 **Liner Removal** ASTM D3330 Specification Results Status 2.3 3.8, Liner Removal, Initial Release 55 N/m Pass

SECTION 3.9Storage StabilitySpecificationResultsStatus3.9, Storage Stability, Liner Removal after 12 Months Below 32°CNo Appreciable DifferenceNot TestedTBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

2-14-2012 Page 1 of 1