250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B

SUPPORT: **EPDM FOAM**

SUBSTRATE: PP

221209 - 0838 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



1378.8

938.1

Pass

Pass

TAPE REQUIREMENTS:

SECTION 3.6.1 Peel Adhesion **ASTM D3330 Specification Results Status Pass**

219 N/m 910.1 3.6.1, Peel Adhesion, As Received, Initial RT

SECTION 3.6.2 **Specification** Results Aged **ASTM D3330 Status**

3.6.2, Aged, Aged, 72 hrs @ RT 657 N/m

SECTION 3.6.3 Aged, Cycles **Specification ASTM D3330** Results **Status**

438 N/m

3.6.3, Aged, Cycles, CycleTest (5x)

4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C

16 hrs @ -29° C

SECTION 3.7 **Migration Stain** FLTM BO 115-1* Specification Results **Status**

Not Applicable 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel None NA

SECTION 3.8 **Liner Removal Specification** Results **ASTM D3330 Status**

3.8, Liner Removal, Initial Release 55 N/m 20.4 **Pass**

SECTION 3.9 **Storage Stability Specification** Results **Status**

No Appreciable Difference Not Tested **TBD** 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

CERTIFIED BY:

1-1-25 ISSUE DATE: Jake Cowdrick, Automotive Application Specialist

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date:

5-11-2005

Page 1 of 1