

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT:	FT B EZ
SUPPORT:	NITRILE VINYL FOAM
SUBSTRATE:	ABS
CERT NO.:	221209 - 0841

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



	MENTS:				
SECTION 3.6.1	Peel Adhesion	ASTM D3330	Specification	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT			219 N/m	1049.0	Pass
SECTION 3.6.2	Aged	ASTM D3330	Specification	Results	<u>Status</u>
3.6.2, Aged, Age	d, 72 hrs @ RT		657 N/m	1300.6	Pass
SECTION 3.6.3	Aged, Cycles	ASTM D3330	Specification	Results	Status
	es, CycleTest (5x)	ASTM D3330	438 N / m	1050.2	Pass
	4 hrs @ 70° C		400 117111	1000.2	1 433
	4 hrs @ 38° C / 95% RH				
	16 hrs @ -29° C				
	4 hrs @ 38° C / 95% RH				
	4 hrs @ 70º C				
	16 hrs @ -29º C				
	Minuting Otain			Branka	e ()
SECTION 3.7	Migration Stain	FLTM BO 115-1*	Specification	Results	<u>Status</u>
3.7, Migration Sta	iin, 48 Hour Fluorescence, White I	Enamel	None	Not Applicable	NA
SECTION 3.8	Liner Removal	ASTM D3330	Specification	Results	Status
3.8, Liner Remov	al, Initial Release		55 N/m	15.8	Pass
SECTION 3.9	Storage Stability		Specification	Results	Status

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

No Appreciable Difference

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Not Tested

TBD

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 5-11-2005 Page 1 of 1