TEST REPORT



250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

PRODUCT: FT B SUPPORT: **FELT** SUBSTRATE: ABS

221209 - 0903 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA

ACCBEDITED TESTING LABORATORY

Status

Pass

Status

Pass

Status

Pass

Status

NA

Status

Pass

Status

TBD

Results

840.6

Results

920.6

Results

767.6

Results

Not Applicable

Results

21.6

Results

Not Tested

TAPE REQUIREMENTS:

SECTION: 3.6.1 **Peel Adhesion ASTM D3330 Specification**

219 N/m 3.6.1, Peel Adhesion, As Received, Initial RT

SECTION: 3.6.2 Aged **ASTM D3330** Specification

3.6.2, Aged, Aged, 72 hrs @ RT

Specification SECTION 3.6.3 Aged, Cycles **ASTM D3330**

3.6.3, Aged, Cycles, CycleTest (5x)

4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C

16 hrs @ -29° C

SECTION: 3.7 **Migration Stain**

FLTM BO 115-1*

3.7, Migration Stain, 48 Hour Fluorescence, White Enamel

Liner Removal SECTION: 3.8

3.8, Liner Removal, Initial Release

SECTION: 3.9 **Storage Stability**

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

ASTM D3330

Specification No Appreciable Difference

657 N/m

438 N/m

Specification

None

Specification

55 N/m

ISSUE DATE: 1-1-25

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.