250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B SUPPORT: **FELT**

SUBSTRATE: PAINTED METAL 221209 - 0903 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

3.6.2, Aged, Aged, 72 hrs @ RT

SECTION: 3.6.1 **Peel Adhesion ASTM D3330 Specification**

219 N/m 3.6.1, Peel Adhesion, As Received, Initial RT

Results 792.2

872.7

Results

882.1

SECTION: 3.6.2 Aged **ASTM D3330** Specification

657 N/m

Specification

438 N/m

Results **Status**

Status

Pass

Pass

Status

Pass

NA

Status

Pass

SECTION 3.6.3 Aged, Cycles **ASTM D3330**

3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C

16 hrs @ -29° C

SECTION: 3.7 FLTM BO 115-1* **Migration Stain**

Specification None

Results **Status**

3.7, Migration Stain, 48 Hour Fluorescence, White Enamel

Liner Removal

ASTM D3330

3.8, Liner Removal, Initial Release

Specification 55 N/m

Results 21.6

SECTION: 3.9 **Storage Stability**

Specification 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference

Results Not Tested

Page 1 of 1

Not Applicable

Status TBD

CERTIFIED BY:

SECTION: 3.8

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

11-26-2014

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.