

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

## **TEST REPORT**

PRODUCT:	FT B
SUPPORT:	FELT
SUBSTRATE:	PP
CERT NO .:	221209 - 0903

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:				
SECTION: 3.6.1 Peel Adh	esion ASTM D3330	<b>Specification</b>	Results	Status
3.6.1, Peel Adhesion, As Rece	eived, Initial RT	219 N/m	807.3	Pass
SECTION: 3.6.2 Aged	ASTM D3330	<b>Specification</b>	Results	<u>Status</u>
3.6.2, Aged, Aged, 72 hrs @ F	RT	657 N/m	979.5	Pass
SECTION : 3.6.3 Aged, Cy	cles ASTM D3330	Specification	Results	<u>Status</u>
3.6.3, Aged, Cycles, CycleTes	st (5x)	438 N/m	1019.8	Pass
4 hrs @	70° C			
4 hrs @	38° C / 95% RH			
16 hrs @ ·	-29° C			
4 hrs @	38° C / 95% RH			
4 hrs @	70° C			
16 hrs @ -	-29° C			
SECTION 3.7 Migration	Stain FLTM BO 115-1*	Specification	Results	Status
3.7, Migration Stain, 48 Hour F	Fluorescence, White Enamel	None	Not Applicable	NA
SECTION 3.8 Liner Ren	noval ASTM D3330	Specification	Results	<u>Status</u>
3.8, Liner Removal, Initial Rele	ease	55 N/m	21.6	Pass

SECTION : 3.9Storage Stability3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

Specification
No Appreciable Difference

ication Results le Difference Not Tested

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Status

TBD

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

 Avery Dennison Performance Tapes
 250 Chester St.
 Painesville, Ohio
 44077
 Original Test Date:
 11-26-2014
 Page 1 of 1