



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 0900X 12 PT BD**
SUPPORT: **FLOCK**
SUBSTRATE: **ABS**
CERT NO.: **230823 - 0649**
FORD ESB M6G17-A
OEM Rev Date: Jul 12
Adhesion Requirements, PSA Antisqueak Flock



NOT FOR NEW DESIGN - NO REPLACEMENT

TAPE REQUIREMENTS:

SECTION: 3.5 Fogging, Oil Bath

3.5, Fogging, Oil Bath, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification
80 Units

FLTM BO 116-3*

Results
100.5

Status
Result

SECTION : 3.6.1 Flock Fiber

As Reported By Supplier

3.6.1, Flock Fiber, Type
3.6.1, Flock Fiber, Size
3.6.1, Flock Fiber, Color
3.6.1, Flock Fiber, Method of Dyeing

Specification
100% Nylon
1.5 - 3.0 Denier
Black
Stock or Solution

Results
100% Nylon
1.5 - 3.0 Denier
Black
Solution

Status
Pass
Pass
Pass
Pass

SECTION : 3.6.2 Flock Adhesive

3.6.2, Statement

The adhesive shall be non-staining and shall be compatible in color with the flock fiber. The adhesive shall not become soft, tacky or exhibit blistering or delamination after any of the tests outlined in this specification, and shall be equal in other properties to the approved sample on file in the Interior Materials Engineering Section.

Specification

Results

This product meets spec criteria

Status
Pass

SECTION : 3.6.3 Fabric

3.6.3, Composition

Specification
50% Synthetic
Woven or non-woven

Results

This product meets spec criteria
This product meets spec criteria

Status
Pass
Pass

SECTION : 3.6.4 Pressure Sensitive Adhesive

3.6.4, Statement

Non-Staining, Heat Resistant and Suitable for a Variety of Substrates

Specification

Results

This product meets spec criteria

Status
Pass

SECTION : 3.7 Thickness

As Reported By Supplier

3.7, Thickness, Flock

Specification
1.35 - 1.60 mm

SAE J882*

Results
0.81

Status
Reported

SECTION : 3.8 Loose Flock

As Reported By Supplier

3.7, Loose Flock

Specification
0.8 g/m2

FLTM BN 8-8*

Results
0.03

Status
Pass

SECTION : 3.9 Abrasion Resistance

As Reported By Supplier

3.9.1, Dry Cycle, CS-10, 1000 g
3.9.2, Wet Cycle (15 min soak), CS-10, 500 g
3.9.3, Heat Aged, 7 days @ 80°C, CS-10, 1000 g

Specification
> 1500 Cycles
> 1000 Cycles
>1500 Cycles

FLTM BN 8-2*

Results
> 1,500
> 1,000
> 1,500

Status
Pass
Pass
Pass

SECTION : 3.10 Scuffing Resistance

As Reported By Supplier

3.1, Scuffing Resistance, 900 g, "A" Head, 2000 Cycles

No Excessive Lifting Of Flock Fibers Or Adhesive Peeling

Specification

FLTM BN 8-4*

Results

The Sample Meets The Standard Requirement

Status
Pass

SECTION : 3.11 Peel Adhesion

3.11.1, Initial, 20 mins @ RT
3.11.2, High Temp, 7 days @ 82°C
3.11.3, Cycles (5X)
4 hrs @ 70°C
4 hrs @ 38°C / 95-100% RH
16 hrs @ -29C

Specification
4 N / cm
11.6 N / cm
14 N / cm

ASTM D1000

Results
17.5
15.6
14.8

Status
Pass
Pass
Pass

SECTION : 3.12 Shear Adhesion

3.12.1, Cold Shear, 24 hrs @ -18°C
3.12.2, Hot Shear, 24 hrs @ 60°C

Specification
232 kPa
89 kPa

ASTM D1000

Results
486.7
248.1

Status
Pass
Pass

SECTION : 3.13 RH Resistance

3.13.1, 48 hrs @ 38°C / 95-100% RH

Specification
No Adhesion Loss

Results

Good, Stable, No Lifting

Status
Pass

SECTION : 3.14 Heat Resistance

3.14.1, 30 mins @ 120°C
3.14.2, 7 days @ 102°C

Specification
No Blistering or Delamination
No Blistering or Delamination

Results

No Blisters or Delamination
No Blisters or Delamination

Status
Pass
Pass

SECTION: 3.15 Odor

3.15, Odor, Dry - 1 hr @ 65°C

Specification
3 Max Rating

SAE J1351*

Results

No Disagreeable Odor, 2

Status
Pass

SECTION: 3.16 Flammability

3.16, Initial, Component

Specification
100 mm / min

ISO 3795* / SAE J369*

Results
< B 25

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

