



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126
SUPPORT: 0.5 MM FELT
SUBSTRATE: ABS
CERT NO.: 221209 - 1100



FORD ESB M6G17-A
OEM Rev Date: Jul 12
Adhesion Requirements, PSA Antisqueak Flock

NOT FOR NEW DESIGN - NO REPLACEMENT

TAPE REQUIREMENTS:

SECTION: **3.5 Fogging** Specification FLTM BO 116- Results Status
3.5, Fogging, Oil Bath, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT **80 Units** 101.0 **Pass**

SECTION **3.11 Peel Adhesion** Specification ASTM D1000 Results Status
3.11.1, Initial, 20 mins @ RT **4 N / cm** 9.3 **Pass**
3.11.2, High Temp, 7 days @ 82°C **11.6 N / cm** 11.0 Tear **Pass**
3.11.3, Cycles (5X) **14 N / cm** 14.5 Tear **Pass**
4 hrs @ 70°C
4 hrs @ 38°C / 95-100% RH
16 hrs @ -29C

SECTION **3.12 Shear Adhesion** Specification ASTM D1000 Results Status
3.12.1, Cold Shear, 24 hrs @ -18°C **232 kPa** 166 Tear **Pass**
3.12.2, Hot Shear, 24 hrs @ 60°C **89 kPa** 162 Tear **Pass**

SECTION **3.13 RH Resistance** Specification Results Status
3.13.1, 48 hrs @ 38°C / 95-100% RH **No Adhesion Loss** Good, Stable, No Lifting **Pass**

SECTION **3.14 Heat Resistance** Specification Results Status
3.14.1, 30 mins @ 120°C **No Blistering or Delamination** No Blisters or Delamination **Pass**
3.14.2, 7 days @ 102°C **No Blistering or Delamination** No Blisters or Delamination **Pass**

SECTION: **3.15 Odor** Specification SAE J1351 Results Status
3.15, Odor, Dry - 1 hr @ 65°C **2 Max Rating** Not Perceptible, 1 **Pass**

SECTION: **3.16 Flammability** Specification ISO 3795 / SAE J369 Results Status
3.16, Initial, Component **100 mm / min** SE **Pass**

CERTIFIED BY:


Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.