



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392
SUPPORT: LOW PERM FOAM
SUBSTRATE: SS
CERT NO.: 221213 - 0744



FORD ESH-M11P19-B
OEM Rev Date: Mar 93
Adhesion Requirements, Cellular Rubber / Polyurethane Foam
Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.1 Peel Strength

3.1.1, As Received

ASTM D3330

Specification

0.44 N / mm

Results

1.29

Status

Pass

SECTION 3.1 Peel Strength

3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification

0.44 N / mm

Results

1.61

Status

Pass

SECTION 3.1 Peel Strength

3.1.2, Humidity, 7 days @ 37°C / 95% RH

Specification

0.44 N / mm

Results

0.89

Status

Pass

SECTION 3.2 Peel Strength

3.2, Foam to Plastic Membrane, As Received

Specification

No Delamination

Results

Foam Tearing

Status

Pass

SECTION 3.3 Bond Separation

3.3, 200 gram load, 1 hr @ RT

ASTM D3330

Specification

No Separation of Bond

Results

No Slip

Status

Pass

SECTION 3.4 Quality

3.4, Quality

Specification

Readily Removable

Results

Easily Removed

Status

Pass

SECTION 3.5 Bacteria / Fungus Resistance

3.5, Bacteria / Fungus Resistance

Specification

Must Pass

Results

All Passed

Status

Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.