



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

### TEST REPORT

PRODUCT: FBD 8393  
 SUPPORT: Polyester Urethane Foam  
 SUBSTRATE: TPO  
 CERT NO.: 240130 - 0603




**FORD ESH-M11P19-B**  
 OEM Rev Date: Jan 13  
 Adhesion Requirements, Cellular Rubber / Polyurethane Foam  
 Pressure Sensitive Film with Biocide

**TAPE REQUIREMENTS:**

**3 Requirements**

SECTION	Requirements	ASTM	Specification	Results	Status
SECTION 3.1	<b>Peel Strength</b>	ASTM D903	<b>0.44 N / mm</b>	1.66	<b>Pass</b>
3.1.1,	As Received				
SECTION 3.1	<b>Peel Strength</b>	ASTM D903	<b>0.44 N / mm</b>	1.10	<b>Pass</b>
3.1.2,	Aged, Heat Aged, 7 days @ 88°C				
SPEC: 3.1	<b>Peel Strength</b>	ASTM D903	<b>0.44 N / mm</b>	1.18	<b>Pass</b>
3.1.2,	Humidity, 7 days @ 37°C / 95% RH				
SECTION 3.2	<b>Peel Strength</b>	ASTM D903	<b>No Delamination</b>	Foam Tearing	<b>Pass</b>
3.2.1,	Foam to Plastic Membrane, As Received				
SECTION 3.3	<b>Bond Separation</b>	ASTM D903	<b>No Separation of Bond</b>	No Slip	<b>Pass</b>
3.3,	200 gram load, 1 hr @ RT				

CERTIFIED BY:   
 David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.  
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.