|  | J |
|--|---|
|--|---|

TAPE REQUIREMENTS:

psa.tape@averydennison.com

tapes.averydennison.com

email:

URL:

## **TEST REPORT**

|                         | DENNISON                    | PRODUCT:<br>SUPPORT: | FBD 8970 12 PT BD<br>PET FOAM |
|-------------------------|-----------------------------|----------------------|-------------------------------|
| 250 Chester Street      |                             | SUBSTRATE:           | PP                            |
| Painesville, Ohio 44077 |                             | CERT NO .:           | 221213 - 0745                 |
| Phone:                  | 866-GO-AVERY (866-462-8379) |                      |                               |
| Fax:                    | 888-358-4469                | FORD ESH-M11P19-B    |                               |



FORD ESH-M11P19-B

OEM Rev Date: Mar 93 Adhesion Requirements, Cellular Rubber / Polyurethane Foam Pressure Sensitive Film with Biocide

| 3 Requirements<br>SECTION 3.1 Peel Strength<br>3.1.1, As Received | ASTM D3330 | Specification<br>0.44 N / mm   | <u>Results</u><br>0.93 | <u>Status</u><br>Pass |
|---|------------|--|------------------------|-----------------------|
| SECTION <b>3.1 Peel Strength</b>                                  | ASTM D3330 | Specification  | <u>Results</u>         | <u>Status</u>         |
| 3.1.2, Aged, Heat Aged, 7 days @ 88°C                             |            | 0.44 N / mm  | 1.05                   | Pass                  |
| SECTION <b>3.1 Peel Strength</b>                                  | ASTM D3330 | Specification  | <u>Results</u>         | <u>Status</u>         |
| 3.1.2, Humidity, 7 days @ 37°C / 95% RH                           |            | 0.44 N / mm  | 1.21                   | Pass                  |
| SECTION <b>3.2 Peel Strength</b>                                  | ASTM D3330 | Specification  | <u>Results</u>         | <u>Status</u>         |
| 3.2, Foam to Plastic Membrane, As Received                        |            | No Delamination  | Foam Tearing           | Pass                  |
| SECTION 3.3 Bond Separation                                       | ASTM D1000 | Specification  | <u>Results</u>         | <u>Status</u>         |
| 3.3, 200 gram load, 1 hr @ RT                                     |            | No Separation of Bond  | No Slip                | Pass                  |
| SECTION 3.4 Quality   |            | Specification  | <u>Results</u>         | <u>Status</u>         |
| 3.4, Quality  |            | Readily Removable  | Easily Removed         | Pass                  |
| SECTION 3.5 Bacteria / Fungus Resis                               | tance      | Specification  | <u>Results</u>         | <u>Status</u>         |
| 3.5, Bacteria / Fungus Resistance                                 |            | Must Pass  | Not Tested             | NT                    |
| CERTIFIED BY: Dave Nichols Jr, Automotive Lab Te                  | 1/         | ISSUE DATE:  | <u>1-1-25</u>          |                       |
|   |            | H +/- 5%. Test uncertainty and minor exclusions are full, without the written approval of the Avery Denn |                        | est.                  |

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*. Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 1-15-2012 Page 1 of 1