

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FBD 8970** SUPPORT: **PET FOAM**

SUBSTRATE: PP

221213 - 0745 CERT NO .:



OEM Rev Date: Mar 93

Adhesion Requirements, Cellular Rubber / Polyurethane Foam

Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.1 ASTM D3330 **Specification Results Peel Strength Status** 0.44 N/mm 1.20 **Pass**

3.1.1, As Received

SECTION 3.1 **ASTM D3330 Specification** Results **Peel Strength** Status

3.1.2, Aged, Heat Aged, 7 days @ 88°C

0.44 N/mm 1.20 **Pass**

SECTION 3.1 **Peel Strength Specification ASTM D3330** Results **Status**

3.1.2, Humidity, 7 days @ 37°C / 95% RH 0.44 N/mm 1.36 **Pass**

SECTION 3.2 ASTM D3330 **Specification Results Peel Strength Status No Delamination** 3.2, Foam to Plastic Membrane, As Received Foam Tearing

SECTION 3.3 **Bond Separation ASTM D1000 Specification Results** Status 3.3, 200 gram load, 1 hr @ RT No Slip No Separation of Bond **Pass**

Specification Results SECTION 3.4 Quality **Status**

3.4, Quality Readily Removable Easily Removed **Pass**

SECTION 3.5 **Bacteria / Fungus Resistance Specification** Results Status 3.5, Bacteria / Fungus Resistance **Must Pass** Not Tested NT

ISSUE DATE: **CERTIFIED BY:** 1-1-25

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

1-15-2012

ANSI National Accreditation Board

ACCREDITED

TESTING LABORATORY

Pass