

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FBD 8970** SUPPORT: **PEU FOAM** SUBSTRATE: PAINTED METAL 221213 - 0745 CERT NO .:



1.76

Pass

FORD ESH-M11P19-B

OEM Rev Date: Mar 93

Adhesion Requirements, Cellular Rubber / Polyurethane Foam

0.44 N/mm

Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.1 ASTM D3330 **Specification Results Peel Strength Status** 0.44 N/mm 1.09 **Pass**

3.1.1, As Received

SECTION 3.1 **ASTM D3330 Specification** Results **Peel Strength** Status

3.1.2, Aged, Heat Aged, 7 days @ 88°C

SECTION 3.1 **Peel Strength Specification** Results **ASTM D3330 Status**

3.1.2, Humidity, 7 days @ 37°C / 95% RH

0.44 N/mm 1.11 **Pass**

SECTION 3.2 ASTM D3330 **Specification Results Peel Strength Status** 3.2, Foam Rubber to Plastic Membrane, As Received **No Delamination** Foam Tearing **Pass**

SECTION 3.3 **Bond Separation ASTM D1000 Specification Results** Status

3.3, 200 gram load, 1 hr @ RT No Slip No Separation of Bond **Pass**

Specification Results SECTION 3.4 Quality **Status**

3.4, Quality Readily Removable Easily Removed **Pass**

SECTION 3.5 **Bacteria / Fungus Resistance Specification** Results Status 3.5, Bacteria / Fungus Resistance **Must Pass** Not Tested NT

ISSUE DATE: **CERTIFIED BY:** 1-1-25

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date:

1-15-2012

Page 1 of 1