



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

### TEST REPORT

PRODUCT: **A5079A**  
SUPPORT: **2 MIL PET**  
SUBSTRATE: **PP**  
CERT NO.: **230109 - 1056**



**FORD ESH-M11P19-B**  
OEM Rev Date: Jan 13  
Adhesion Requirements, Cellular Rubber / Polyurethane Foam  
Pressure Sensitive Film with Biocide

*Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.*

#### TAPE REQUIREMENTS:

#### 3 Requirements

SECTION	Requirements	ASTM D903	Specification	Results	Status
3.1	<b>Peel Strength</b>				
3.1.1	As Received		<b>0.44 N / mm</b>	0.49	<b>Pass</b>
3.1.2	Aged, Heat Aged, 7 days @ 88°C		<b>0.44 N / mm</b>	0.52	<b>Pass</b>
SPEC:	<b>3.1 Peel Strength</b>				
3.1.2	Humidity, 7 days @ 37°C / 95% RH		<b>0.44 N / mm</b>	0.63	<b>Pass</b>
3.2	<b>Peel Strength</b>				
3.2.1	Foam to Plastic Membrane, As Received		<b>No Delamination</b>	Cohesive	<b>Pass</b>
3.3	<b>Bond Separation</b>				
3.3	200 gram load, 1 hr @ RT		<b>No Separation of Bond</b>	No Slip	<b>Pass</b>

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.