



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **C690B**
SUPPORT: **2 MIL PET**
SUBSTRATE: **PP**
CERT NO.: **230109 - 1056**



FORD ESH-M11P19-B
OEM Rev Date: Jan 13
Adhesion Requirements, Cellular Rubber / Polyurethane Foam
Pressure Sensitive Film with Biocide

Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.

TAPE REQUIREMENTS:

3 Requirements

SECTION	Requirements	ASTM D903	Specification	Results	Status
3.1	Peel Strength				
3.1.1,	As Received		0.44 N / mm	0.95	Pass
3.1.2,	Aged, Heat Aged, 7 days @ 88°C		0.44 N / mm	0.96	Pass
SPEC:	3.1 Peel Strength				
3.1.2,	Humidity, 7 days @ 37°C / 95% RH		0.44 N / mm	1.02	Pass
3.2	Peel Strength				
3.2.1,	Foam to Plastic Membrane, As Received		No Delamination	Cohesive	Pass
3.3	Bond Separation				
3.3,	200 gram load, 1 hr @ RT		No Separation of Bond	No Slip	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.