

TEST REPORT

| | DENNISON | PRODUCT: SUPPORT: | FBD 8970 PET FOAM | |
|--------------------|-----------------------------|-----------------------|-----------------------|--|
| 250 Chester Street | | SUBSTRATE: | PP | |
| Painesvil | le, Ohio 44077 | CERT NO .: | 221213 - 0756 | |
| Phone: | 866-GO-AVERY (866-462-8379) | | | |
| Fax: | 888-358-4469 | FORD ESH-M11P40-A | | |
| email: | psa.tape@averydennison.com | OEM Rev Date: | Sep 87 | |
| URL: | tapes.averydennison.com | Adhesion Requirements | | |
| | | Pressure Sensit | ive Film with Biocide | |
| | | | | |
| | | | | |



TAPE REQUIREMENTS:

| 3 Requirements SECTION 3.2 Peel Strength, Plastic Membrane to Panel 3.2.1, As Received | Specification 0.22 N / mm | ASTM D3330 | Results 1.20 | <u>Status</u> Pass |
|--|------------------------------|------------|------------------------|-----------------------|
| SECTION 3.2 Peel Strength, Plastic Membrane to Panel 3.2.2, Aged, Heat Aged, 7 days @ 88°C | Specification 0.22 N/mm | ASTM D3330 | <u>Results</u> 1.20 | <u>Status</u> Pass |
| SECTION 3.2 Peel Strength, Plastic Membrane to Panel | Specification | ASTM D3330 | <u>Results</u> | <u>Status</u> |
| 3.2.2, Humidity, 7 days @ 37°C / 95% RH | 0.11 N / mm | | 1.36 | Pass |
| SECTION 3.3 Peel Strength | Specification | ASTM D3330 | <u>Results</u> | <u>Status</u> |
| 3.3.1, Foam to Plastic Membrane, As Received | No Delamination | | Foam Tearing | Pass |
| SECTION 3.4 Bond Separation | Specification | ASTM D1000 | <u>Results</u> | <u>Status</u> |
| 3.4, 200 gram load, 1 hr @ RT | No Separation of Bond | | No Slip | Pass |
| SECTION 3.5 Quality | Specification | | <u>Results</u> | <u>Status</u> |
| 3.5, Quality | Readily Removable | | Easily Removed | Pass |

SECTION 3.6 Bacteria / Fungus Resistance 3.6, Bacteria / Fungus Resistance

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

Specification Must Pass

Not Tested

Results

Pass

Status

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 1-15-2012 Page 1 of 1