



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392 12 PT BD
SUPPORT: PEU FOAM
SUBSTRATE: PP
CERT NO.: 221213 - 0807



FORD WSA-M11P19-C
OEM Rev Date: Jul 93
Adhesion Requirements, Polyurethane Foam
Pressure Sensitive Adhesive, High Tack

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.4 Peel Strength

3.4.1, As Received

Specification
0.88 N / mm

ASTM D3330

Results
0.97

Status
Pass

SECTION 3.4 Peel Strength

3.4.2, Heat Aged, 7 days @ 88°C

Specification
0.88 N / mm

ASTM D3330

Results
1.20

Status
Pass

SECTION 3.4 Peel Strength

3.4.2, Humidity, 7 days @ 37°C / 95% RH

Specification
0.88 N / mm

ASTM D3330

Results
1.27

Status
Pass

SECTION 3.5 Peel Strength

3.5.1, Foam to Plastic Membrane, As Received

Specification
Foam Tear

ASTM D3330

Results
Foam Tearing

Status
Pass

SECTION 3.6 Creep Adhesion

3.6, 200 gram load, 1 hr @ RT

Specification
6.4 mm

Results
No Slip

Status
Pass

CERTIFIED BY:

[Signature]

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.