

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com


URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FM 2454 SUPPORT: ABS

SUBSTRATE:

221213 - 0809 CERT NO.:



OEM Rev Date: Feb 91

Adhesive Requirements, Exterior Rear View Mirror Applications

5.1.3 SS



TAPE REQUIREMENTS: SECTION: 3.4 Shear Adhesi 3.4.1 , Shear Adhesion, 30 mins (Specification 690 kPa	<u>Results</u> 730.8	<u>Status</u> Pass
3.4.2, Shear Adhesion, 30 mins @	-30° C, No recovery	830 kPa	986.6	Pass
3.4.3, Shear Adhesion, 336 hrs @	90°C	690 kPa	592.2	Pass
3.4.4, Shear Adhesion, 30 mins @	. 120°C	690 kPa	546.3	Pass
3.4.5, Shear Adhesion, 120 hrs De	ei-Water Immersed @ 60°C	410 kPa	607.3	Pass
4 h 16 h 4 h 4 h	k) rs @ 90°C rs @ 38°C / 95% RH rs @ -30°C rs @ 38°C / 95% RH rs @ 90°C rs @ 90°C	690 kPa	646.2	Pass
3.4.7, Shear Adhesion, 260 kJ/m2	Xenon Arc Exposure SAE J1960	Not Tested	Not Tested	Not Testec

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Original Test Date:

5-9-2017

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.