



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

**TEST REPORT**


PRODUCT: **FT 8397**  
SUPPORT: **EPDM FOAM**  
SUBSTRATE: **SS**  
CERT NO.: **221213 - 0809**



**FORD WSB M3G212-A**  
OEM Rev Date: Feb 06  
Tape, Low Density EPDM Foam, Pressure Sensitive, Supersoft

**TAPE REQUIREMENTS:**

SECTION:	ASTM D1000	Specification	Results	Status
<b>3.12 Pressure Sensitive Adhesion</b>				
3.12.1, Adhesion to Stainless Steel		<b>500 N / m</b>	786.3	<b>Pass</b>
3.12.2, Adhesion to Painted Metal		<b>500 N / m</b>	642.7	<b>Pass</b>
<b>SECTION 3.12 Adhesion to Stainless Steel</b>		<b>Specification</b>	<b>Results</b>	<b>Status</b>
3.12.3, Adhesion, 30 mins @ 120°C, Inverted		<b>No Adhesion Loss or Failure</b>	Good, Stable, No Lifting	<b>Pass</b>
3.12.3, Adhesion, Environmental Cycling 5x, Inverted 16 hrs @ 38°C / 95-100% RH 4 hrs @ -30C 4 hrs @ 90°C		<b>No Adhesion Loss or Failure</b>	Good, Stable, No Lifting	<b>Pass</b>
<b>SECTION: 3.14 Fogging</b>	SAE J1756	<b>Specification</b>	<b>Results</b>	<b>Status</b>
3.14, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT		<b>60 Units</b>	89.8	<b>Pass</b>
<b>SECTION 3.15 Heat Shrink Resistance</b>		<b>Specification</b>	<b>Results</b>	<b>Status</b>
3.15, 21 days @ 121°C, Painted Metal - % Height Loss		<b>&lt; 10% All Directions</b> Height	0%	<b>Pass</b>
3.15, 21 days @ 121°C, Painted Metal - % Height Loss		<b>&lt; 10% All Directions</b> Width	3%	<b>Pass</b>
3.15, 21 days @ 121°C, Painted Metal - % Height Loss		<b>&lt; 10% All Directions</b> Length	2%	<b>Pass</b>
<b>SECTION: 3.16 Liner Removal</b>	ASTM D1000	<b>Specification</b>	<b>Results</b>	<b>Status</b>
3.16, Liner Removal, Initial, Room Temp		<b>2 - 11 N / m</b>	8.8	<b>Pass</b>

CERTIFIED BY:   
**Dave Nichols Jr, Automotive Lab Technician**

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.  
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.