## **TEST REPORT**



250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

FT 1143 PRODUCT: SUPPORT: **UHMWPE** PAINTED METAL SUBSTRATE:

CERT NO.: 221213 - 0809



OEM Rev Date: Aug 06

Tape, Polyethylene, PSA, Interior - Exterior



| TAPE REQUIREMENTS: SECTION: 3.7 Adhesion 3.7.1.1, Adhesion, As Received, 48 hrs @ RT 3.7.2.1, Adhesion, Cycles (5x) 4 hrs @ 70°C 4 hrs @ 38°C / 95-100% F | ASTM D1000                         | Specification<br>350 N/m<br>526 N/m      | Results<br>873.3<br>1012.3   | Status<br>Pass<br>Pass             |
|---|------------------------------------|--|--|------------------------------------|
| 16 hrs @ -30C<br>3.7.2.2, Adhesion, Water Immersion, 240 hrs<br>3.7.2.2, Adhesion, Salt Spray, 240 hrs<br>3.7.2.2, Adhesion, Xenon Weatherometer, 400 hr  | FLTM BN 104-01*<br>FLTM BN 103-01* | 526 N/m<br>526 N/m<br>526 N/m            | 1446.6<br>1099.2<br>Not Tested   | Pass<br>Pass<br>Not Tested         |
| SECTION 3.8 Resistance Properties 3.8.1, RH, 7 days @ 38°C / 95-100% RH 3.8.2, Heat and Cold Resistance (5x) 2 hrs @ 100°C 2 hrs @ -30°C                  | No Adhesio                         | ification<br>n Loss, Curl or<br>nination | Results Stable, No Lifting, Delmanination or Edge Curl Stable, No Lifting, Delmanination or Edge Curl  | Status<br>Pass<br>Pass             |
| 3.8.3, Heat Resistance, 30 mins @ 120°C 3.8.4, Water Immersion, 240 hrs 3.8.5, Salt Spray, 240 hrs 3.8.6, Xenon Weatherometer, 400 hrs                    |                                    |  | Stable, No Lifting, Delmanination or Edge Curl<br>Stable, No Lifting, Delmanination or Edge Curl<br>Stable, No Lifting, Delmanination or Edge Curl<br>Not Tested | Pass<br>Pass<br>Pass<br>Not Tested |
| SECTION 3.9 Heat Aging 3.9, 7 days @ 80°C   | No Edge Cur                        | ification<br>I, Stain or Color<br>nange  | Results Good, No Color Changing, Staining or Edge Curl   | <u>Status</u><br>Pass              |
| SECTION <b>3.10</b> Shrink 3.10, 30 mins @ 120°C  |                                    | Specification 1 % max                    | <u>Results</u><br>Not Tested   | <u>Status</u><br>Not Tested        |
| SECTION: <b>3.11 Fogging</b> 3.11, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ R  | г                                  | Specification<br>60 Units                | Results<br>98.00   | Status<br>Pass                     |
| SECTION 3.12 Abrasion Resistance<br>3.12, CS-10, 1000 g Load - 1500 Cycles  |                                    | Specification > No Wear Thru             | <u>Results</u><br>NoT tested   | <u>Status</u><br>Not Tested        |
| SECTION 3.13 Scuffing Resistance<br>3.13, 900 g Load, "A" Head - 1500 Cycles  |                                    | Specification  o Cracking or Peeli       | <u>Results</u><br>Not Tested   | Status<br>Not Tested               |
| SECTION <b>3.14</b> Resistance to Fade 3.14, 225.6 kJ/m2 Exposure   |                                    | Specification<br>4 Rating min            | <u>Evaluation</u><br>Not Tested  | Status<br>Not Tested               |
| SECTION 3.15 Exterior Xenon Weatheron 3.15, 400 hrs @ 70°C  | neter Resistance                   | Specification<br>4 Rating Min            | Results Not Tested   | Status<br>Not Tested               |
| SECTION: <b>3.16</b> Flammability 3.16, Initial, Component  |                                    | Specification<br>100 mm / min            | <u>Results</u>   | Status<br>Pass                     |
| SECTION: <b>3.18 Odor</b> 3.18, Odor, Dry - 1 hr @ 65°C   | SAE J1351*                         | Specification 2 Rating max               | <u>Results</u><br>No Disagreeable Odor, 2  | Status<br>Pass                     |

CERTIFIED BY:

ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Dave Nichols Jr, Automotive Lab Technician

1-1-25