



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT B**
 SUPPORT: **RUBBER**
 SUBSTRATE: **PAINTED METAL**
 CERT NO.: **221213 - 0810**



FORD WSF-M11P8-A2
 OEM Rev Date: Jan 92
 Adhesion Requirements

Sponge Rubber, High Tack

TAPE REQUIREMENTS:

3 Requirements
 SECTION **3.3 Adhesion**
 3.3.1, As Received

ASTM D903

Specification
0.88 N / mm

Results
 1.19

Status
Pass

SECTION **3.3.2 Adhesion**
 3.3.2.1, Heat Aged, 14 days @ 88°C

ASTM D903

Specification
0.33 N / mm

Results
 0.96

Status
Pass

SECTION **3.3.2 Adhesion**
 3.3.2.1, Humidity, 14 days @ 37°C / 95% RH

ASTM D903

Specification
0.66 N / mm

Results
 1.73

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.