



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 0900X
 SUPPORT: FLOCK
 SUBSTRATE: PP
 CERT NO.: 230105 - 0913



FORD WSS-M11P62-A

OEM Rev Date: Jun 07

Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.5 Odor
 3.5, 1 hr @ 65°C, Dry

SAE J1351*

Specification
 2 Rating

Results
 2 - Slight, But Noticeable Odor

Status
 Pass

3.5,1 hr @ 65°C, Wet

2 Rating

2 - Slight, But Noticeable Odor

Pass

SECTION: 3.4 Flammability
 3.4, Flammability, Initial, Component

SAE J369

Specification
 100 mm / min

Results
 < B25

Status
 Pass

SECTION: 3.6 Fogging, Oil Bath
 3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756 06

Specification
 70 Units

Results
 93.8

Status
 Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

98.6

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.