



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 0900X PET  
 SUPPORT: FLOCK  
 SUBSTRATE: ABS  
 CERT NO.: 221213 - 0914



**FORD WSS-M11P62-A**  
 OEM Rev Date: Jun 07

Performance Requirements for Adhesives Used in Interior Applications  
 Assembly Performance Parts Below the Belt Line

**TAPE REQUIREMENTS:**

SECTION: 3.5 Odor\*  
 3.5, 1 hr @ 65°C, Dry

SAE J1351\*

Specification  
 2 Rating

Results  
 2 - Slight, But Noticeable Odor

Status  
 Pass

3.5,1 hr @ 65°C, Wet

2 Rating

2 - Slight, But Noticeable Odor

Pass

SECTION: 3.4 Flammability  
 3.4, Flammability, Initial, Component

SAE J369

Specification  
 100 mm / min

Results  
 < B25

Status  
 Pass

SECTION: 3.6 Fogging, Oil Bath  
 3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756 06

Specification  
 70 Units

Results  
 96.1

Status  
 Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

99.2

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.