

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 8217 SUPPORT: 2 mm FELT

SUBSTRATE: ABS 221213 - 0902

CERT NO .:

FORD WSS-M11P62-A OEM Rev Date: Jun 07

Performance Requirements for Adhesives Used in Interior Applications

ACCREDITED

TESTING LABORATORY

1-1-25

Page 1 of 1

11-12-2012

ISSUE DATE:

Original Test Date:

Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

Odor SECTION: 3.5 SAE J1351\* **Specification** Results **Status** 2 Rating 2 - Slight, But Noticeable Odor 3.15, 1 hr @ 65°C, Dry **Pass** 

3.15, 1 hr @ 65°C, Wet 2 Rating 2 - Slight, But Noticeable Odor **Pass** 

Results SECTION: 3.4 **Flammability** SAE J369 **Specification Status** < B 18 3.4, Flammability, Initial, Component 100 mm / min **Pass** 

Results SECTION: 3.6 **Fogging SAE J1756 Specification Status** 81.9 3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT 70 Units **Pass** 

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT 70 Units 100.0 **Pass** 

Jake Cowdrick, Automotive Application Specialist

**CERTIFIED BY:** 

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.