



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8327**
 SUPPORT: **PET FABRIC**
 SUBSTRATE: **40% TALC PP**
 CERT NO.: **221213 - 0911**



FORD WSS-M11P62-A
 OEM Rev Date: Jul 05
 Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

SECTION:	SAE	Specification	Results	Status
3.5 Odor 3.5 Odor, 1 hr @ 65°C - Dry	SAE J1351*	2 Rating	2 - Slight, But Noticeable Odor	Pass
3.5 Odor, 1 hr @ 65°C - Wet		2 Rating	2 - Slight, But Noticeable Odor	Pass
3.4 Flammability 3.4, Flammability, Initial, Component	SAE J369	100 mm / min	< B25	Pass
3.6 Fogging 3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT	SAE J1756	70 Units	84.1	Pass
3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT		70 Units	100.9	Pass

CERTIFIED BY: 
 Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.