



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392
SUPPORT: PET FIBER
SUBSTRATE: PP
CERT NO.: 221213 - 0911



FORD WSS-M11P62-A
OEM Rev Date: Jun 07
Performance Requirements for Adhesives Used in Interior Applications
Assembly Performance Parts At or Above the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.5 Odor
3.5, 1 hr @ 65°C, Dry

SAE J1351*

Specification
2 Rating

Results
1 - No Noticeable Odor

Status
Pass

3.5,1 hr @ 65°C, Wet

2 Rating

1 - No Noticeable Odor

Pass

SECTION: 3.4 Flammability
3.4, Flammability, Initial, Component

SAE J369

Specification
100 mm / min

Results
< B 25

Status
Pass

SECTION: 3.6 Fogging
3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756

Specification
70 Units

Results
103.1

Status
Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

100.5

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.