



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392
 SUPPORT: RED FLOCK
 SUBSTRATE: PP
 CERT NO.: 221213 - 0911



FORD WSS-M11P62-A
 OEM Rev Date: Jun 07
 Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts At or Above the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.5 Odor	SAE J1351*	<u>Specification</u> 2 Rating	<u>Results</u> 2 - Slight, But Noticeable Odor	<u>Status</u> Pass
3.5, 1 hr @ 65°C, Dry				

3.5, 1 hr @ 65°C, Wet		2 Rating	2 - Slight, But Noticeable Odor	Pass
-----------------------	--	-----------------	---------------------------------	-------------

SECTION: 3.4 Flammability	SAE J369	<u>Specification</u> 100 mm / min	<u>Results</u> < B25	<u>Status</u> Pass
3.4, Flammability, Initial, Component				

SECTION: 3.6 Fogging	SAE J1756	<u>Specification</u> 70 Units	<u>Results</u> 100	<u>Status</u> Pass
3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT				

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT		70 Units	100	Pass
---	--	-----------------	-----	-------------

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.