



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8393 12 PT BD
SUPPORT: FLOCK
SUBSTRATE: ABS
CERT NO.: 231005 - 0621



FORD WSS-M11P62-A
OEM Rev Date: Jun 07
Performance Requirements for Adhesives Used in Interior Applications
Assembly Performance Parts At or Above the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.4 Flammability ISO 3795 / SAE J369 Specification 100 mm / min Results < B 25 Status Pass

SECTION: 3.5 Odor SAE J1351 Specification 2 Rating Results 2 - Slight, But Noticeable Odor Status Pass

3.5 Odor, 1 hr @ 65°C - Wet 2 Rating Results 2 - Slight, But Noticeable Odor Status Pass

SECTION: 3.6 Fogging, Oil Bath SAE J1756 Specification 70 Units Results 70.1 Status Pass

3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT 70 Units Results 94.3 Status Pass

CERTIFIED BY: [Signature]
David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.