



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT


PRODUCT: **FT A902**
 SUPPORT: **FLOCK**
 SUBSTRATE: **PP**
 CERT NO.: **240808 - 0508**



FORD WSS-M11P62-A
 OEM Rev Date: Jun 07
 Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts At or Above the Belt Line

TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
3.4 Flammability 3.4, Initial, Component	ISO 3795 / SAE J369 100 mm / min	SE	Pass
3.5 Odor 3.5 Odor, 1 hr @ 65°C - Dry	SAE J1351 2 Rating	Not Tested	Not Tested
3.5 Odor, 1 hr @ 65°C - Wet	2 Rating	Not Tested	Not Tested
3.6 Fogging, Oil Bath 3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT	SAE J1756 70 Units	50.3	Fail
3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT	70 Units	77.9	Pass

CERTIFIED BY: 
 David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.