



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 0900X PET  
 SUPPORT: FLOCK  
 SUBSTRATE: ABS  
 CERT NO.: 240114 - 1027



**FORD WSS-M11P68-A1**  
 OEM Rev Date: Jan 20  
 Tape, Performance, Pressure Sensitive Adhesive One-Sided, Interior  
 Scuff Plate / Floor Area

**TAPE REQUIREMENTS:**

**3. Requirements**

**SECTION: 3.5 Thickness**

3.5 Thickness - Complete Product Composite

Specification	Results	Status
FLTM BO 131-03* Reported mm	0.91	Reported

**SECTION: 3.6 Weight**

3.6 Weight - Complete Product Composite 100 cm<sup>2</sup>

Specification	Results	Status
FLTM BO 131-03* Reported g / m <sup>2</sup>	3.423	Reported

**SECTION: 3.7 Breaking Strength, Tape**

3.7 Breaking Strength, Tape

Specification	Results	Status
FLTM BO 131-03* Reported N / 10 mm	85.90	Reported

**SECTION: 3.8 Fogging**

3.8 Fogging - Photometric, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification	Results	Status
FLTM BO 131-03* 70 Units min	74.9	Pass

**SECTION: 3.9 Odor**

3.9.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

Specification	Results	Status
FLTM BO 131-03* Rating 3 Max	Not Tested	Not Tested

3.9.2 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

Rating 3 Max	Not Tested	Not Tested
--------------	------------	------------

3.9.3 Odor, Condition 3 - 2 hrs @ 65°C

Rating 3 Max	Not Tested	Not Tested
--------------	------------	------------

**SECTION: 3.10 Flammability**

3.2.3 Initial, Component

Specification	Results	Status
SAE J369* < 100 mm / min	< B 25	Pass

**SECTION: 3.11 Adhesion Strength**

3.11 Original

Specification	Results	Mode	Status
ASTM D1000 300 N / m	910.1	CLN	Pass

3.11.2 After Short Term Environment Cycling

5 hrs @ -30°C  
 30 mins @ 23°C / 50%RH  
 5 hrs @ 80°C  
 30 mins @ 23°C / 50%RH  
 2 hrs @ 50°C / 95%RH  
 30 mins @ 23°C / 50%RH  
 5 hrs @ -30°C  
 30 mins @ 23°C / 50%RH  
 5 hrs @ 80°C

FLTM BO 140-01 A* 225 N / m	1682.5	TRN	Pass
--------------------------------	--------	-----	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

FLTM BO 140-01 B* 225 N / m	1817.6	SP	Pass
--------------------------------	--------	----	------

**SECTION: 3.11 Adhesion Strength**

3.11 Original

Specification	Results	Status
No Cracking, Blistering, Adhesion Loss or Delamination	Good, Stable, No Defects or Lifting	Pass

3.11.2 After Short Term Environment Cycling

Good, Stable, No Defects or Lifting	Good, Stable, No Defects or Lifting	Pass
-------------------------------------	-------------------------------------	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

Good, Stable, No Defects or Lifting	Good, Stable, No Defects or Lifting	Pass
-------------------------------------	-------------------------------------	------

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.