



**TEST REPORT**

250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

PRODUCT: FBR 8950 12 PT BD  
SUPPORT: PET FOAM  
SUBSTRATE: TPO  
CERT NO.: 221213 - 1015



**FORD WSS-M11P68-A1**  
OEM Rev Date: Jan 20  
Tape, Performance, Pressure Sensitive Adhesive One-Sided, Interior Scuff Plate / Floor Area

**TAPE REQUIREMENTS:**

**3. Requirements**

SECTION: **3.5 Thickness**  
3.5 Thickness

FLTM BO 131-03*	<b>Specification</b> Reported mm	<b>Results</b> 47.2	<b>Status</b> Reported
-----------------	-------------------------------------	------------------------	---------------------------

SECTION: **3.6 Weight**  
3.6 Weight

FLTM BO 131-03*	<b>Specification</b> Reported g / m <sup>2</sup>	<b>Results</b> 5.336	<b>Status</b> Reported
-----------------	---	-------------------------	---------------------------

SECTION: **3.7 Breaking Strength**  
3.7 Breaking Strength

FLTM BO 131-03*	<b>Specification</b> Reported N / 10 mm	<b>Results</b> 20.45	<b>Status</b> Reported
-----------------	--	-------------------------	---------------------------

SECTION: **3.8 Fogging**  
3.8 Fogging - Photometric, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

FLTM BO 131-03*	<b>Specification</b> 70 Units min	<b>Results</b> 98	<b>Status</b> Pass
-----------------	--------------------------------------	----------------------	-----------------------

SECTION: **3.9 Odor**  
3.9.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

FLTM BO 131-03*	<b>Specification</b> Rating 3 Max	<b>Results</b> Not Perceptible, 1	<b>Status</b> Pass
-----------------	--------------------------------------	--------------------------------------	-----------------------

3.9.2 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

Rating 3 Max	Perceptible, Not Disturbing, 2	Pass
--------------	--------------------------------	------

3.9.3 Odor, Condition 3 - 2 hrs @ 65°C

Rating 3 Max	Perceptible, Not Disturbing, 2	Pass
--------------	--------------------------------	------

SECTION: **3.10 Flammability**  
3.2.3 Initial, Component

SAE J369*	<b>Specification</b> < 100 mm / min	<b>Results</b> 25.0	<b>Status</b> Pass
-----------	--	------------------------	-----------------------

SECTION: **3.11 Adhesion Strength**  
3.11 Original

ASTM D1000	<b>Specification</b> 300 N / m	<b>Results</b> 1248.9	<b>Mode</b> CSP	<b>Status</b> Pass
------------	-----------------------------------	--------------------------	--------------------	-----------------------

3.11.2 After Short Term Environment Cycling  
5 hrs @ -30°C  
30 mins @ 23°C / 50%RH  
5 hrs @ 80°C  
30 mins @ 23°C / 50%RH  
2 hrs @ 50°C / 95%RH  
30 mins @ 23°C / 50%RH  
5 hrs @ -30°C  
30 mins @ 23°C / 50%RH  
5 hrs @ 80°C

FLTM BO 140-01 A*	<b>225 N / m</b>	2185.2	CSP	Pass
-------------------	------------------	--------	-----	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

FLTM BO 140-01 B*	<b>225 N / m</b>	1501.5	L CSP	Pass
-------------------	------------------	--------	-------	------

SECTION: **3.11 Adhesion Strength**  
3.11 Original

<b>Specification</b> No Cracking, Blistering, Adhesion Loss or Delamination	<b>Results</b> Good, Stable, No Defects or Lifting	<b>Status</b> Pass
--	---	-----------------------

3.11.2 After Short Term Environment Cycling

Good, Stable, No Defects or Lifting	Pass
-------------------------------------	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

Good, Stable, No Defects or Lifting	Pass
-------------------------------------	------

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.